

Casing

Size Designation	Weight Designation lb/ft	Outside Diameter		Wall Thickness		Type of End Finish							
		In.	mm	In.	mm	Grade							
						H-40	J-55 K-55	M-65	L-80 C-95	N-80	C-90 T-95	P-110	Q-125
4 1/2"	9.5	4.500	114.30	0.205	5.21	PS	PS	PS	--	--	--	--	--
	10.50	4.500	114.30	0.224	5.69	--	PSB	PSB	--	--	--	--	--
	11.60	4.500	114.30	0.250	6.35	--	PSLB	PLB	PLB	PLB	PLB	PLB	--
	13.50	4.500	114.30	0.290	7.37	--	--	PLB	PLB	PLB	PLB	PLB	--
	15.10	4.500	114.30	0.337	8.56	--	--	--	--	--	--	PLB	PLB
5"	11.50	5.000	127.00	0.220	5.59	--	PS	PS	--	--	--	--	--
	13.00	5.000	127.00	0.253	6.43	--	PSLB	PSLB	--	--	--	--	--
	15.00	5.000	127.00	0.296	7.52	--	PSLB	PLB	PLB	PLB	PLB	PLB	--
	18.00	5.000	127.00	0.362	9.19	--	--	PLB	PLB	PLB	PLB	PLB	PLB
	21.40	5.000	127.00	0.437	11.10	--	--	PLB	PLB	PLB	PLB	PLB	PLB
	23.20	5.000	127.00	0.478	12.14	--	--	--	PLB	PLB	PLB	PLB	PLB
	24.10	5.000	127.00	0.500	12.70	--	--	--	PLB	PLB	PLB	PLB	PLB
5 1/2"	14.00	5.500	139.70	0.244	6.20	PS	PS	PS	--	--	--	--	--
	15.50	5.500	139.70	0.275	6.98	--	PSLB	PSLB	--	--	--	--	--
	17.00	5.500	139.70	0.304	7.72	--	PSLB	PLB	PLB	PLB	PLB	PLB	--


Prime Import & Export Limited Company

	20.00	5.500	139.70	0.361	9.17	--	--	PLB	PLB	PLB	PLB	PLB	--
	23.00	5.500	139.70	0.415	10.54	--	--	PLB	PLB	PLB	PLB	PLB	PLB
	26.80	5.500	139.70	0.500	12.70	--	--	--	--	--	P	--	--
	29.70	5.500	139.70	0.562	14.27	--	--	--	--	--	P	--	--
	32.60	5.500	139.70	0.625	15.87	--	--	--	--	--	P	--	--
	35.30	5.500	139.70	0.687	17.45	--	--	--	--	--	P	--	--
	38.00	5.500	139.70	0.750	19.05	--	--	--	--	--	P	--	--
	40.50	5.500	139.70	0.812	20.62	--	--	--	--	--	P	--	--
	43.10	5.500	139.70	0.875	22.23	--	--	--	--	--	P	--	--
6 5/8"	20.00	6.625	168.28	0.288	7.32	PS	PSLB	PSLB	--	--	--	--	--
	24.00	6.625	168.28	0.352	8.94	--	PSLB	PLB	PLB	PLB	PLB	PLB	--
	28.00	6.625	168.28	0.417	10.59	--	--	PLB	PLB	PLB	PLB	PLB	--
	32.00	6.625	168.28	0.475	12.06	--	--	--	PLB	PLB	PLB	PLB	PLB
7"	17.00	7.000	177.80	0.231	5.87	PS	--	--	--	--	--	--	--
	20.00	7.000	177.80	0.272	6.91	PS	PS	PS	--	--	--	--	--
	23.00	7.000	177.80	0.317	8.05	--	PSLB	PLB	PLB	PLB	PLB	PLB	--
	26.00	7.000	177.80	0.362	9.19	--	PSLB	PLB	PLB	PLB	PLB	PLB	--
	29.00	7.000	177.80	0.408	10.36	--	--	PLB	PLB	PLB	PLB	PLB	--
	32.00	7.000	177.80	0.453	11.51	--	--	PLB	PLB	PLB	PLB	PLB	--
	35.00	7.000	177.80	0.498	12.65	--	--	--	PLB	PLB	PLB	PLB	PLB
	38.00	7.000	177.80	0.540	13.72	--	--	--	PLB	PLB	PLB	PLB	PLB

Tel: +86-546-3980778, Fax: +86-546-3983778

Email: info@shengli-petroleum.com chinaprime@yahoo.com.cn

<http://www.shengli-petroleum.com>


Prime Import & Export Limited Company

	42.70	7.000	177.80	0.625	15.87	--	--	--	--	--	P	--	--
	46.40	7.000	177.80	0.687	17.45	--	--	--	--	--	P	--	--
	50.10	7.000	177.80	0.750	19.05	--	--	--	--	--	P	--	--
	53.60	7.000	177.80	0.812	20.62	--	--	--	--	--	P	--	--
	57.10	7.000	177.80	0.875	22.23	--	--	--	--	--	P	--	--

7 5/8"	24.00	7.625	193.68	0.300	7.62	PS	--	--	--	--	--	--	--
	26.40	7.625	193.68	0.328	8.33	--	PSLB	PSLB	PLB	PLB	PLB	PLB	--
	29.70	7.625	193.68	0.375	9.53	--	--	PLB	PLB	PLB	PLB	PLB	--
	33.70	7.625	193.68	0.430	10.92	--	--	PLB	PLB	PLB	PLB	PLB	--
	39.00	7.625	193.68	0.500	12.70	--	--	--	PLB	PLB	PLB	PLB	PLB
	42.80	7.625	193.68	0.562	14.27	--	--	--	PLB	PLB	PLB	PLB	PLB
	45.30	7.625	193.68	0.595	15.11	--	--	--	PLB	PLB	PLB	PLB	PLB
	47.10	7.625	193.68	0.625	15.88	--	--	--	PLB	PLB	PLB	PLB	PLB
	51.20	7.625	193.68	0.687	17.45	--	--	--	--	--	P	--	--
	55.30	7.75	193.68	196.85	19.05	--	--	--	--	--	P	--	--
7 3/4"	46.10	8.625	219.08	0.595	15.11	--	--	--	P	P	P	P	P
8 5/8"	24.00	8.625	219.08	0.264	6.71	--	PS	PS	--	--	--	--	--

Tel: +86-546-3980778, Fax: +86-546-3983778

Email: info@shengli-petroleum.com chinaprime@yahoo.com.cn

<http://www.shengli-petroleum.com>


Prime Import & Export Limited Company

	28.00	8.625	219.08	0.304	7.72	PS	--	PS	--	--	--	--	--
	32.00	8.625	219.08	0.352	8.94	PS	PSLB	PSLB	--	--	--	--	--
	36.00	8.625	219.08	0.400	10.16	--	PSLB	PSLB	PLB	PLB	PLB	PSLB	--
	40.00	8.625	219.08	0.450	11.43	--	--	PLB	PLB	PLB	PLB	PLB	--
	44.00	8.625	219.08	0.500	12.70	--	--	PLB	PLB	PLB	PLB	PLB	--
	49.00	9.625	244.48	0.557	14.15	--	--	--	PLB	PLB	PLB	PLB	PLB
9 5/8"	32.30	9.625	244.48	0.312	7.92	PS	--	--	--	--	--	--	--
	36.00	9.625	244.48	0.352	8.94	PS	PSLB	PSLB	--	--	--	--	--
	40.00	9.625	244.48	0.395	10.03	--	PSLB	PSLB	PLB	PLB	PLB	--	--
	43.50	9.625	244.48	0.435	11.05	--	--	PLB	PLB	PLB	PLB	PLB	--
	47.00	9.625	244.48	0.472	11.99	--	--	PLB	PLB	PLB	PLB	PLB	PLB
	53.50	9.625	244.48	0.545	13.84	--	--	--	PLB	PLB	PLB	PLB	PLB
	58.40	9.625	244.48	0.595	15.11	--	--	--	PLB	PLB	PLB	PLB	PLB
	59.40	9.625	244.48	0.609	15.47	--	--	--	--	--	P	--	--
	64.90	9.625	244.48	0.672	17.07	--	--	--	--	--	P	--	--
	70.30	9.625	244.48	0.734	18.64	--	--	--	--	--	P	--	--


Prime Import & Export Limited Company

	75.60	9.625	244.48	0.797	20.24	--	--	--	--	--	P	--	--
--	-------	-------	--------	-------	-------	----	----	----	----	----	---	----	----

10 3/4"	32.75	10.75	273.05	0.279	7.09	PS	--	--	--	--	--	--	--
	40.50	10.75	273.05	0.350	8.89	PS	PSB	PSB	--	--	--	--	--
	45.50	10.75	273.05	0.400	10.16	--	PSB	PSB	--	--	--	--	--
	51.00	10.75	273.05	0.450	11.43	--	PSB	PSB	PSB	PSB	PSB	PSB	--
	55.50	10.75	273.05	0.495	12.57	--	--	PSB	PSB	PSB	PSB	PSB	--
	60.70	10.75	273.05	0.545	13.84	--	--	--	--	--	PSB	PSB	PSB
	65.70	10.75	273.05	0.595	15.11	--	--	--	--	--	PSB	PSB	PSB
	73.20	10.75	273.05	0.672	17.07	--	--	--	--	--	P	--	--
	79.20	10.75	273.05	0.734	18.64	--	--	--	--	--	P	--	--
	85.30	10.75	273.05	0.797	20.24	--	--	--	--	--	P	--	--
11 3/4"	42.00	11.75	298.45	0.333	8.46	PS	--	--	--	--	--	--	--

Tel: +86-546-3980778, Fax: +86-546-3983778
 Email: info@shengli-petroleum.com chinaprime@yahoo.com.cn
<http://www.shengli-petroleum.com>


Prime Import & Export Limited Company

	47.00	11.75	298.45	0.375	9.53	--	PSB	PSB	--	--	--	--	--
	54.00	11.75	298.45	0.435	11.05	--	PSB	PSB	--	--	--	--	--
	60.00	11.75	298.45	0.489	12.42	--	PSB	PSB	PSB	PSB	PSB	PSB	PSB
	65.00	11.75	298.45	0.534	13.56	--	--	--	P	P	P	P	P
	71.00	11.75	298.45	0.582	14.78	--	--	--	P	P	P	P	P
13 3/8"	48.00	13.375	339.73	0.330	8.38	PS	--	--	--	--	--	--	--
	54.50	13.375	339.73	0.380	9.65	--	PSB	PSB	--	--	--	--	--
	61.00	13.375	339.73	0.430	10.92	--	PSB	PSB	--	--	--	--	--
	68.00	13.375	339.73	0.480	12.19	--	PSB	PSB	PSB	PSB	PSB	PSB	--
	72.00	13.375	339.73	0.514	13.06	--	--	--	PSB	PSB	PSB	PSB	PSB



Prime Import & Export Limited Company

18-5/8	87.50	0.435	17.7 55	17. 567	20.0 00	H4																
						0																
						J55																
20	94.00	0.438	19.1 24	18. 936	21.0 00	H4																
						0																
						J55																
	106.50	0.500	19.1 24	18. 936	21.0 0	K5																
						5																
						J55																
133.00	0.635	18.7 30	18. 542	21.0 0	K5																	
					5																	

Outside Diameter, Wall Thickness and Weight Tolerance:

Item		Tolerance
Outside Diameter		D < 114.3mm, ±0.79mm D ≥ 114.3mm, ±1.0~0.5%D
Wall Thickness		-12.5%±
Weight	Single Lengths	+6.5%, -3.5%
	Carloads	-1.75%

Lengths:

Range Name	Range 1	Range 2	Range 3
Tubing	6.10 ~ 7.32 m	8.53 ~ 9.75 m	--
Casing	4.88 ~ 7.62 m	7.62 ~ 10.36 m	10.36 ~ 14.63 m

Chemical Composition:

Grade	Chemical Composition (%)												
	C		Mn		Mo		Cr		Ni	Cu	P	S	Si
	min	max	min	max	min	max	min	max	max	max	max	max	max
J55	---	---	---	---	---	---	---	---	---	---	0.030	0.030	---
K55	---	---	---	---	---	---	---	---	---	---	0.030	0.030	---
N80	---	---	---	---	---	---	---	---	---	---	0.030	0.030	---
M65	---	---	---	---	---	---	---	---	---	---	0.030	0.030	---
L80-1	---	0.43	---	1.90	---	---	---	---	0.25	0.35	0.030	0.030	0.45
C90-1	---	0.35	---	1.00	0.25	0.75	---	1.20	0.99	---	0.020	0.010	---
C90-2	---	0.50	---	1.90	---	NL	---	NL	0.99	---	0.030	0.010	---
C95	---	0.45	---	1.90	---	---	---	---	---	---	0.030	0.030	0.45
T95-1	---	0.35	---	1.20	0.25	0.85	0.40	1.50	0.99	---	0.020	0.010	---
T95-2	---	0.50	---	1.90	---	---	---	---	0.99	---	0.030	0.010	---
P110	---	---	---	---	---	---	---	---	---	---	0.030	0.030	---